



## Instruction Guide For Mixing LM-95

It is critical that the appropriate amount of LM-95 Activator be mixed with the appropriate amount of LM-95. Therefore, each LM-95 product comes packaged with pre-measured quantities of the Part A and Part B (Activator). Each pre-measured container is labeled, defining Part A and Part B, to assist with identifying the appropriate component.

**Storage:** Polyguard recommends the LM-95 be stored in temperatures between 40°F (5°C) and 80°F (27°C); and, if at any time Part B has been frozen, it must be discarded and replaced.

Preparation: All tools and equipment must be clean prior to use.

- *Product Temperature* For best results and lower viscosity, warm-up both components A and B between 50°F (24°C) to 95°F (35°C).
- *Drill Size, Spiral Mixer , Amps/Rpm's* Depending on the size of your project, the drill size, spiral mixer size, and rpm's will remain the same, but the amps required will differ.
  - For small project quantities, the use of a 1/2" drill (at least 5 amp and 500-900 rpm) and an All-Steel 2-1/2 gallon spiral mixer (Fig. 1) is sufficient to thoroughly mix both LM-95 components.
  - For larger project quantities and continuous mixing, use a 1/2" drill (at least 9 amp and 500-900 rpm) or larger and an All-Steel 2-1/2 gallon spiral mixer (Fig. 1) to thoroughly mix both LM-95 components.
- The DO NOTS:
  - use fan blade, mud style or rod style mixers.
  - o use mixing jigs.
  - modify from factory controlled container.
  - $\circ$  thin products.
  - $\circ$  mix water into the pail.
  - $\circ$  mix products by hand.
  - add more or less of either component, A or B. Changing the mix ratio will affect coating and performance.

**Mixing:** When mixing, always start at the bottom of pail, then pull mixer slowly up to about 2/3 of pail (being cautious not to pull up too far causing splatter), then slowly move back down to the bottom of the pail. Repeat this step, however this time, rotate the mixer around the inner edge of pail. Continue this process for both components for the times specified below:

• Using 2-1/2 Gallon Spiral Mixer: Mix Component A thoroughly for 3 minutes, then add Component B to Component A; thoroughly mix for an additional 2 minutes.

NOTE: DO NOT APPLY ANY MATERIAL IF STREAKS CAN BE SEEN DUE TO INSUFFICIENT MIXING.



P.O. Box 755 Ennis, TX 75120 PH: (214) 515-5000 FX: (972) 875-9425 The information contained in this document is based on data and knowledge considered to be true and accurate at time of printing and is offered for the users' consideration, investigation and verification. Polyguard Products, Inc. cannot be held liable for errors made as a result of information herein. Changes and modifications can be made to this document without prior notice. No statement, recommendation or suggestion is intended for use which would infringe on patents or copyrights held by Polyguard Products, Inc.



www.Polyguard.com